

保温耐火，防火隔热，陶瓷纤维纸

产品名称	保温耐火，防火隔热，陶瓷纤维纸
公司名称	富阳海利尔纤维有限公司
价格	38000.00/吨
规格参数	耐火温度:1000-1350 () 规格:0.5-6 (mm) 产地:富阳
公司地址	杭州富阳区银湖街道受降村大树下
联系电话	86 0571 63417982/63417981 13706818352

产品详情

耐火温度	1000-1350 ()	规格	0.5-6 (mm)
产地	富阳	品牌	海利尔
产品类别	硅酸铝制品	材质	陶瓷纤维
导热系数 (常温)	0.35	等级	优
使用温度	1000 ° 1260 ° 1350 °	芯材	陶瓷纤维
形态	纤维状	形状	卷状

以陶瓷纤维为主原料，采用湿法成型工艺制成，具有耐高温耐化学腐蚀耐热冲击，导热系数低，高电绝缘强度和高弹性模具等性能。强度大，容重小，弹性好等特点，随意裁切缠绕，施工操作简便，是一种高级轻质耐火材料。型号:1350,1260,1000等，厚度0.5-6mm，幅宽600mm - 1000mm，型号厚度幅宽可根据具体要求定做，以纸箱包装为主。应用范围：1.隔热密封垫 2.电热器隔热绝缘材料 3.汽车消音器、排气管的消音隔热材料 4.高温隔热材料 5.膨胀缝密封材料

	标准型	高铝型
品名name	standapaper	highaluminapaper
项目item型号type	stdz	haz
颜色color	白white	白white
分类温度 ()		
classificationtemperature()	1260	1350
工作温度 ()		

maximum operating temperature ()	1000	1200
容量 (平均) (kg/m ³)		
bulk density(kg/m ³)	190 ± 20	200 ± 20
抗拉强度 (mpa)		
tensile strength (mpa)	0.65	0.75
有机物含量 (%)		
organic matter content (%)	8	7
导热系统 (w/m.k)		
thermal conductivity(w/m.k)	800 0.195	800 0.19
加热线收缩率 (%)		
reeling line shrinkage(%)	1000 *24h 3.5	1000 *24 3.0
化学成分 (%) typical chemical composition (%)		
al ₂ o ₃	46	50
sio ₂	50	48
fe ₂ o ₃	1.0	0.2
	厚度0.5-8	宽度350-1000
规格 (mm)	thickness0.5-8	width350-1000
standard(mm)	可按用户设计要求加工 in accordance with design drawing of user manufactured	

以上数据为产品的平均值，不应视为保证值，产品验收按国标或签约合同执行。

the data compiled represents average properties and should not be considered to be guaranteed specifications. the products are checked and accepted in accordance with the standards of our country and signed contract.

add : 浙江省富阳市高桥开发区 tel : 0571-63417982 fax : 0571-63417983 http:www.hailier.com.cn