



Rapid and complete de-watering.

???????????

Firm, greasy coating is resistant to removal during handling.

????????????????????

Good resistant to emulsification.

???????

Easy to remove with solvents or aqueous cleaner.

????????????????

Good anti-salted property.

?????????

Technical Properties(?????):

Test測試	Unit 單位	Typical 結果
Density密度@15	kg/l	0.765
Flash Point閃點	° C	50
Coverage覆蓋範圍	m2/L	65
Film Thickness油膜厚度	micron	5
Drying Time乾涸時間@21	mins	30
(95%溶劑, Solvent)		
Appearance顏色 :	--	Pale Yellow 淡黃色