

# 可再分散乳胶粉 璟宝

产品名称	可再分散乳胶粉 璟宝
公司名称	湖州璟宝新型建材有限公司
价格	.00/个
规格参数	型号: J B - 0 1 J B - 0 2 品牌:璟宝
公司地址	湖州市杨家埠镇果木园路118号-1
联系电话	86-05722700168 13857290875

## 产品详情

型号 J B - 0 1 J B - 0 2 品牌 璟宝

可再分散性乳胶粉jb-01

re-dispersible emulsion powder jb-01

jb-01是一种乙酸乙烯酯—乙烯(vac/e)共聚的可再分散性乳胶粉

jb-01 is a type re-dispersible emulsion powder copolymerized with vac/e

理化性能 physical and chemical properties

外观可流动白色粉末

appearance white powder flow

残余水分 2.0%

residual moisture 2.0%

平均粒度(μm)约80

average particle diameter(μm) approx. 80

堆积密度(g/l) 420 ~ 600

stacking density ( g/l ) 420 ~ 600

灰分(1000 ) (10 ± 2)%

ash content (1000 ) (10 ± 2)%

50%水溶液粘度 ( 25 pa ) 0.5 ~ 3.0

viscosity of 50% water solution(25 pa)0.5 ~ 3.0

ph值 5.0 ~ 7.0

ph value 5.0 ~ 7.0

最低成膜温度0

lowest membrane-forming temperature0

安全性无毒

securitynontoxic

建议应用范围suggestion application scope

1.外墙外保温抹面砂浆used in interface mortar for exterior insuiation

2.外墙柔性腻子used as soft putty for exterior walls of building

3.对柔韧性有较高要求的水泥基聚合物砂浆产品used in flexibility-demanding cement-based polymer mortar products

特性features

该产品属柔软型乳胶粉，可在水中分散，提高砂浆与普遍支撑物间的粘着力，改善砂浆机械性能，增强砂浆的可施工性。

soft emulsion powder ,disp in water ,increase the adhesion between mortar and its substrates,and improve the mechanic property and manageability of mortar.

包装package

三合一纸塑复合袋。每袋净重25kg.

compound triple paper-plastic package,every sack of this product weighs 25 kg

贮存storage

30 以下和防潮环境中贮存stored at dampproof places below 30

保质期valid period

180天。如超过保质期产品无结块仍可使用。

180 days out of this valid period, if not agglomerated, this product can still be usable

可再分散性乳胶粉jb-02

## re-dispersible emulsion powder jb-02

---

jb-02是一种乙酸乙烯酯—乙烯(vac/e)共聚的可再分散性乳胶粉

jb-02 is a type re-dispersible emulsion powder copolymerized with vac/e

理化性能 physical and chemical properties

外观可流动白色粉末

appearance white powder flow

残余水分 2.0%

residual moisture 2.0%

平均粒度(μm) 约80

average particle diameter(μm) approx. 80

堆积密度(g/l) 420 ~ 600

stacking density (g/l) 420 ~ 600

灰分(1000℃) (12 ± 2)%

ash content (12 ± 2)%

50%水溶液粘度(25℃) 0.5 ~ 3.0

viscosity of 50% water solution (25℃) 0.5 ~ 3.0

ph值 5.0 ~ 7.0

ph value 5.0 ~ 7.0

最低成膜温度 0

lowest membrane-forming temperature 0

安全性 无毒

securitynontoxic

建议应用范围suggestion application scope

1.干粉界面剂used as interface dry powder

2.瓷砖粘结剂used as ceramic tile cohering dose

3.对柔韧性有较高要求的水泥基聚合物砂浆产品used in flexibility-demanding cement-based polymer mortar products

特性features

该产品属柔软型乳胶粉，可在水中分散，提高砂浆与普遍支撑物间的粘着力，改善砂浆机械性能，增强砂浆的可施工性。

soft emulsion powder ,disp in water ,increase the adhesion between mortar and its substrates,and improve the mechanic property and manageability of mortar.

包装package

三合一纸塑复合袋。每袋净重25kg.

compound triple paper-plastic package,every sack of this product weighs 25 kg

贮存storage

30 以下和防潮环境中贮存stored at dampproof places below 30

保质期valid period

180天．如超过保质期产品无结块仍可使用。

180das.out of this valid period,if not agglomerated,this product can still be usable