

# 高电压内胶外纤套管 昆矽

产品名称	高电压内胶外纤套管 昆矽
公司名称	上海昆矽绝缘材料厂
价格	.00/米
规格参数	是否提供加工定制:是 品牌:昆矽 型号:FRS-70
公司地址	上海市松江区小昆山镇山西路46号
联系电话	86 021 13386063208 13917534882

## 产品详情

是否提供加工定制	是	品牌	昆矽
型号	FRS-70	材质	硅橡胶
阻燃性	阻燃	耐温	200 ( )
耐压	7.0 (KV)	颜色	白、黑等
产品认证	SGS UL		

品牌昆矽	型号frs-70
材质硅橡胶	阻燃性阻燃
耐温200 ( )	耐压7 (kv)
颜色各种颜色	产品认证ul rohs

硅橡胶玻璃纤维(内胶外纤)套管，是由硅橡胶挤出成管后，外加

于编织玻璃纤维再经涂以硅树脂高温处理而成，具有极好的绝缘

耐温保护作用，同样广泛应用于h &n级电机、家用电器、电热

设备、特种灯具等绝缘保护。

silicone rubber fiberglass (rubber inside and fiber outside) sleeving, forms sleeving by extruding silicone rubber, adds woven fiberglass and coated with silicone resin in high temperature. it has superb insulation and heat resistance protection, widely used in the insulation protection of internal line cluster in h&n machinery, household electrical appliances, electroheat device and special illuminations.

技术指标：体积电阻: 10 cm 自熄时间：10秒

technical index: volume resistance: 10 cm off-self time: 10 seconds

型号	测试条件	耐燃烧性	耐温	平均电压
type	test condition	lighting-resistance	temperature-resistance	average voltage
frs-70	ul1441	ul vw-1	+200 -60	7000v

性能参数specification

项目item	性能指标value
连续使用温度范围continuous operating temperature	-10 +200
耐高温性 temperature endurance	200 ± 2 168?1/2原电压值
热老化 aging test	260 、6小时、无裂纹
冷弯曲 cold bend	无裂纹
水平燃烧 horizontal flame test	< 30秒
燃烧 (vw-1) flame retardance	< 30秒
水解稳定性 submerge water test	不发粘、不变形、不软化

内径尺寸inside diameter measurement :

内径inside diameter		壁厚wall thickness
标称nominal	公差tolerance	
1.0~2.5mm	+0.20-0.00mm	0.80 ± 0.05mm
3.0~5.5mm	+0.30-0.00mm	0.90 ± 0.05mm
6.0~7.0mm	+0.35-0.00mm	1.00 ± 0.05mm
8.0~9.0mm	+0.40-0.00mm	1.10 ± 0.05mm
10.0~12.0mm	+0.50-0.00mm	1.25 ± 0.05mm