

4047铝药芯焊丝 JCW

产品名称	4047铝药芯焊丝 JCW
公司名称	苏州金鸿焊接材料有限公司
价格	.00/个
规格参数	型号:JCW 类型:药芯 品牌:JINHONG
公司地址	苏州工业园区港田路99号
联系电话	86 0512 67201597 13328008762

产品详情

型号	JCW	类型	药芯
品牌	JINHONG	助焊剂含量	15 - 20 (%)
标准直径	2.2; 2.0 (mm)	熔点	577 ()
重量	2 0 0 0 (g)	用途	铝及铝合金焊接
材质	4047 4045	产地	中国
长度	10000	工作温度	610
规格	1.6、 1.8、 2.0、 2.2、 2.4	焊接电流	0
牌号	JINHONG	是否含助焊剂	是

铝及铝合金焊接用

水箱、冷凝器、蒸发器等铝热交换器的钎焊过程中，
需要修补及管接头的焊接，药芯焊丝是非常好用的焊接材料。尤其对薄壁管的焊接是必不可少的焊材。

本公司生产的药芯焊丝，选用质量上佳的德国产进口
苏威焊剂，采用国内先进的生产工艺精心制造而成。

产品规格多种多样：

焊丝材质 4047 4045

焊接母材纯铝 3003 6061 6063

焊丝直径 1.6 1.8 2.0 2.2 2.4 mm

也可按客户所需或要求定制。

jinhong's aluminum flux cored wire is aa 4047 aluminum braze alloy, cored with non-corrosive nocolok® flux, and is used for joining aluminum and aluminum alloys.

aa 4047 aluminum is the eutectic aluminum/silicon composition that melts over the narrow temperature range of 1070 ° f-1080 ° f (577 ° c to 582 ° c). normal brazing temperature is 1080 ° f-1120 ° f (582 ° to 604 ° c).

nocolok® flux and its residues are non-hygroscopic and non-corrosive, eliminating post braze cleaning.

standard wire diameters are .1.8m, 2.0mm, 2.2mm,2.4mm.

specifications

alloy: nocolok® flux:

aws a5.8 baysi-4k1-3alf4-6alcoa 718melting range:aa 4047 1040 ° f-1070 ° fams 4185 (560 ° c - 577 ° c)

nominal composition:88% ai - 12% si

melting range:1070 ° f-1080 ° f(577 ° c - 582 ° c)