

EVA 台湾台聚 UE659 热融级

产品名称	EVA 台湾台聚 UE659 热融级
公司名称	东莞市文腾塑胶原料有限公司
价格	16.00/kg
规格参数	品牌:台湾台聚 型号:UE659 产地:热融级
公司地址	广东省东莞市樟木头镇先威68号塑金塑胶商业中心14栋203室
联系电话	0769-82933715 18128593518

产品详情

EVA 台湾台聚 UE659 热融级

Excellent soldering resistance makes PA6T particularly suitable for surface-mount technology electrical connector. 2. Excellent high temperature rigidity PA6T can maintain quite high modulus at high temperature, such as 55% of modulus

性能项目	试验条件[状态	测试方法	测试数据	数据单位
基本性能	熔体流动速率	ASTM D-1238	2	g/10min
	密度	ASTM D-1505	0.947	g/cm3
机械性能	硬度	ASTM D-2240	31	Shore D
	延展性	铸膜成型	ASTM D-638 (ASTM D-882)	%
		射出	ASTM D-638 (ASTM D-882)	236 %
		薄膜MD	ASTM D-638 (ASTM D-882)	290 %
		薄膜TD	ASTM D-638 (ASTM D-882)	680 %
	低温易脆性	ASTM D-746	< -76	/F50

	冲击强度		ASTM D-1709	444	G/F50
	降伏点抗张强度	铸膜成型	ASTM D-638 (ASTM D-882)	212	KG/cm2
		射出	ASTM D-638 (ASTM D-882)	114	KG/cm2
		薄膜MD	ASTM D-638 (ASTM D-882)	259	KG/cm2
		薄膜TD	ASTM D-638 (ASTM D-882)	240	KG/cm2
热性能	熔点		ASTM D-2117	77	
	维卡软化点		ASTM D-1525	54	
其它性能	VA含量		USIFE	25	%

EVA 台湾台聚 UE659 热融级

Water absorption is low for nylon resin, the water absorption of PA6T is quite low, only 1/4 to 1/3 of Nylon 66. Therefore, the physical properties of PA6T are relatively small due to water absorption. 5. Excellent dimensional stability PA6T water absorption rate is very low, because of water absorption