

# 狮力昂Sliontec UV膜NO.6360-15

产品名称	狮力昂Sliontec UV膜NO.6360-15
公司名称	上海微赋斯电子科技有限公司
价格	.00/个
规格参数	狮力昂:Sliontec UV膜:NO.6360-15 日本:日本
公司地址	上海市闵行区七莘路50号10幢201室
联系电话	021-64929685 18016274100

## 产品详情

上海微赋斯电子科技有限公司是狮力昂UV膜6360系列中国区一级代理商，直接和日本原厂Maxell拿货，质量有保证，价格也非常有优势，型号和尺寸齐全，并且有大量现货，欢迎咨询订购。

UV Dicing Tape:No.6360-15

Standard

Feature:

Non-PVC backing is used

High-Pressure mercury lamp or black light can be used as light source

Isotropic performance at expanding process

Property:

Item No.	No.6360-15
Color	Translucent
Thickness ( um)	Transparent
Liner:38um	150
Peel strength	10
	2.9(0.22)
	SUS

[ N/10mm ] ( ) :After UV	Glass	3.4(0.23)
	SI wafer	3.4(0.28)
Holding Power	40 /24hour	< 0.1mm
Tensile Strength (Before UV)		30/30
(TD/MD) ( N/10mm )		
Elongation (Before UV)		900/840
(TD/MD) ( %/10mm )		

UV irradiation condition : High-pressure mercury lamp, 75mW/cm<sup>2</sup> at 365nm, for 4 sec ( 300mJ/cm<sup>2</sup>)

Peel Strength (90 Peel) : Pass the 2kg roller in each direction at a rate of 300mm/min.

Aging time ; 20min. Rate of peel ; 300mm/min.

Holding power : Pass the 2kg roller in each direction at a rate of 300mm/min. Load ; 1kg/25mm × 25mm

TD : Transverse Direction, MD : Machine Direction