

1184G-A15 Polybutylene Terephthalate (PBT)15% Glass Fiber

产品名称	1184G-A15 Polybutylene Terephthalate (PBT)15% Glass Fiber
公司名称	东莞市辉众塑胶有限公司
价格	.00/个
规格参数	
公司地址	东莞市樟木头镇塑胶原料市场壹期新一栋4号（注册地址）
联系电话	86-0769-82863609 13268638988

产品详情

Physical Properties	Metric	English	Comments
		1.55 g/cc	
Water Absorption		0.070 % @ Time 86400 s	
Linear Mold Shrinkage, Flow		0.0050 cm/cm	
Linear Mold Shrinkage, Transverse		0.012 cm/cm	
Mechanical Properties	Metric	English	Comments
		85	
Tensile Strength		110 MPa	
Elongation at Break		2.5 %	

Tensile Modulus	6.90 GPa
Flexural Strength	170 MPa
Flexural Modulus	6.50 GPa
Charpy Impact Unnotched	3.50 J/cm
Charpy Impact, Notched	0.550 J/cm
Coefficient of Friction	0.15
	0.20
Volume Resistance	5.60e+16 ohm-cm
Dielectric Constant	3.6@Frequency 5000 Hz
	3.8@Frequency 1000 Hz
Dielectric Strength	14.0 kV/mm
Dissipation Factor	0.0020@Frequency 5000 Hz
	0.020@Frequency 1000 Hz
Arc Resistance	135 sec

Comparative Tracking Index

250 - 400 V