

机械性能				
Abrasion2	30	mm		ISO 4649
弹性体				
拉伸应力				DIN 53504
20%应变,23	2.5	MPa		
应变,23	6.00			
300%应变,23	11.5			
拉伸应力(屈服,23)	45.0	DIN 53504		
伸长率(断裂,23)	550	%		
撕裂强度3(23)	60	kN/m		ISO 34-1
压缩变形				
23	26			ISO 815
70	43			
冲击性能				
简支梁缺口冲击强度				ISO 179/1
-30	无断裂			
23				