乳白胶替代品 共振牌 共振牌

产品名称	乳白胶替代品 共振牌 共振牌
公司名称	浙江金华共振粘合剂厂
价格	.00/个
规格参数	型号:共振牌 品牌:共振牌 粘合材料类型:纸张类
公司地址	中国 浙江 金华市 金东区澧浦镇平阳上平路88号
联系电话	86 0579 82837085/82170588/82837087

产品详情

型号 共振牌 品牌 共振牌

粘合材料类型 纸张类

本厂技术部门能按客户使用要求来生产最合适的相应产品。

浙江金华共振粘合剂厂产品符合国家食品卫生、外贸出口包装要求、国际sgs机购检测认证的粘合材料,它无味、无腐蚀、初粘强、干燥快、防潮性好,贮运和使用方便等特点。产品广泛应用于纸箱、纸盒、纸袋、印刷装订、办公用品胶、贴标、铝箔纸等等行业。适用于单面机、纸桶机、卷管机、瓦楞贴面机、贴标机、扑克机、全自动覆面机、半自动覆面机及卡纸对裱、手工覆裱等生产线。它成本低,为淘汰百年来的泡花碱,取代玉米胶和昂贵的白乳胶及聚乙烯醇等粘合材料方面获得巨大成果。本产品让用户降低生产成本、提高生产效率、产品质量和经济效益的新一代产品。

品名	型号	调胶量(t)	备注	
彩盒速干胶	gz-202	4-5	全自动、半自动复面机及卡纸对裱	
聚乙烯醇替代品	gz-201	4-6	全自动、半自动复面机及卡纸对裱	
乳白胶代替品	gz-999	4-6	半自动及手工复裱	
彩合粘合剂	gz-998	4-6	全自动、半自动复面机及卡纸对裱	
注: 首推客户使用彩盒速干胶,其干燥快、挺度好、不反潮等特点。				

主要技术指标符合q/jhyooi——2002企业标准,符合国际环保sgs认证。

外观:白色或乳白灰白等粉末状

气味:无异味(具有加工原料应有气味)

水份:10%—14%

细度:100目筛通过率 98%

ph值:9—11

粘合强度: (n/m楞) 588

粘合剂系列产品特点:

· 施胶量省、成本低:瓦楞纸板双面施胶每平方米90克左右, 而泡花碱需150克左右。

比重轻:本品胶液比重为1:1(水),而泡花碱比重1.7:1(水)。

快干、挺度好:单机裱瓦后30分钟左右即可下道工序,而玉米胶则需数10多小时。 ·

粘合强度:粘合强度为泡花碱的3倍左右。

不返潮、不变色: 瓦楞纸箱成型干燥后不返潮, 不退色, 耐抗压, 无霉烂。

运输方便:固体粉状在上机前随调随用,使用方法与泡花碱一样。

贮存期长:本品贮存在半年不影响使用。 · 卫生标准:符合国家卫生部门和外贸出口的要求。

粘合剂调胶方法:

一吨粉剂可调胶4-8吨左右 ,下面以25kg/包为例: 先将75公斤水倒入容器中,把本品倒入搅拌均匀。然后把包内糊化剂一起倒入另一小容器中,用2公斤水搅拌完全溶解后,再把它慢慢倒入之前的淀粉容器中,搅拌直至液体变浓全都均匀成为胶体后停止搅拌,再等待20分钟左右完全反应,即可使用。

gong zhen adhesive product

the products which are made by zhejiang jinhua gongzhen adhesive factory meet the requirement of state food hygiene, international packing, sgs. there are many features of the adhesive product, such as tasteless, non-corrosive, strong stickiness, fast drying, good moisture resistance, easy for delivery and using, and so on. products are widely used in cardboard boxes, cartons, paper bags, printing and binding, office supplies plastic, labeling, aluminum foil, and so on. apply to single-sided machines, bucket machines, roll pipe machine, corrugated veneer machines, labeling machines, poker machines, automatic cladding machine, semi-automatic laminator and cardboard on the mounted, hand-mounted cover production line.

the cost is low. we have made a great achievement in the aspect of adhesive material to disuse alkali, replace corn plastic, white latex and poval.

this product lower the producing cost, improve producing efficiency, quality and economic efficiency.

—, the main technical indicators in line with q/jhyooi--2002 enterprise standards, in line with international sgs environmental protection test.

appearance: white or milky gray-white in powder

odour: no odour (with the smell of raw materials)

moisture: 10%—15%

fineness: 100 mesh sieve pass rate 98%

ph value: 9—11

adhesive strength (n / m lenz) 588

二、starch mixture series (powder) adjusting the glue methods:

type	tune the	remark
4	amount of	
	glue (t)	
gz-202	45	fully automatic, semi-automatic machines a
		cardboard on the complex surface mount
gz-201	45	fully automatic, semi-automatic machines a
		cardboard on the complex surface mount
gz-999	56	e-type corrugated machine automatically re
		surface and surface mounted cardboard rig
gz-998	6	corrugated cardboard stand-alone complex s
	gz-202 gz-201 gz-999	amount of glue (t) gz-202

one ton powder can be transferred to 4-7tonsadhesive. for example by 25kg/ bag as following:

first 75 kg of water into the container, put this product into the mix evenly. and then pasting agent package with a small container into the other with 2 kg of water, mixing completely dissolved, then stir it slowly into the starch in the container, stirring until the liquid thickens to cease all evenly into colloidal stirring, and then wait for about 20 minutes a complete response, you can use.

三、main products:

zhejiang jinhua gongzhen adhesive factory

address: no.88 shangping road, lipu town, jinhua city, zhejiang province

legal representative: gong jingjian

zip: 321000tel:: 0579-82837085

bank: agricultural bank of china in jinhua fax: 0579-82170588

account: 610101040001610contact person: 13806785356