

粘度指数改进剂RHY-612

产品名称	粘度指数改进剂RHY-612
公司名称	江门市江海区出光橡塑化工有限公司
价格	.00/个
规格参数	型号:612 品牌:-- 产品规格:--
公司地址	中国 广东 江门市 高新技术开发区东升路20号
联系电话	86 0750 3807990

产品详情

型号	612	品牌	--
产品规格	--	执行标准	--
CAS	--		

viscosity index improver: rhy-612

the viscosity index improver rhy-612 of hong kong ' s aowaseda petrochemical co.,ltd is produced from the dual ethylene-propylene rubber as raw materials, hot melted in 150sn with certain proportion . the product has excellent thickening ability,good thermal stability and low temperature performance,issuitable for lubricating oil with low shear stability requirements to be viscosity index improver and tackifier, the quality of products meet the petrochina lubricating oil company products rhy-612 product standards.

physical and chemical properties

item uint test method targets typical data

appearanc yellowish or yellow transparent sticky liquid

color class gb/t6540 2.0 1.5

movement viscosity of 100 mm2/s gb/t265 1200 1282

thickening capacity mm2/s sh/t0566 6.0 6.4

diesel nozzle shear stability indexssi% q/sy rh4001 50 48.38

floc point (open) gb/t3536 170 192

ppd parameter sh/t0622-07 appendix d report 20

moisture m% gb/t260 0.06 traces

mechanical impurities m% gb/t511 0.08 0.042

low apparent viscosity (-20 ccs) mpa.s q/sy rh3001-02 appendix b report 3050

notes

to concocting the product, the maximum temperature should not exceed 80 , if long-term storage of the product, the temperature should not exceed 50 , product barrel weight 170kgs.

manufacturer:

hong kong aowaseda petrochemical co.,ltd

guangdong representative office: no.20 dongsheng road, jiangmen city, guangdong province, china.

contacts: mr.li guofei

mob: 86 13902887300

tel : 86 750-3807990

fax : 86 750-3809993

粘度指数改进剂： rhy-612

香港奥莱斯特石化有限公司生产的粘度指数改进剂rhy-612,是采用二元乙丙橡胶为原料，以一定比例热熔于150sn中制成。产品具有优良的增稠能力，较好的热稳定性及低温性能，适用于剪切安定性要求不高的润滑油产品做粘度指数改进剂和增粘剂，产品质量满足中国石油润滑油公司rhy-612产品指标。

理化性质

项目 单位测试方法 指标 典型数据

外观 目测浅黄色或黄色透明粘稠液体

颜色 级 gb/t6540 2.0 1.5

运动粘度100 mm²/s gb/t265 1200 1282

稠化能力 mm²/s q/sy rh4001 6.0 6.4

柴油喷嘴剪切稳定性指数ssi % q/sy rh3001附录a 50 48.38

闪点（开口）， gb/t3536 170 192

降凝度参数， sh/t0622-07附录d 报告 20

水分 m% gb/t260 0.06 痕迹

机械杂质 m% gb/t511 0.08 0.042

低温表观粘度（-20 ccs） mpa.s q/sy rh3001-02附录b 报告 3050

注意事项

调和产品时，温度最高不应超过80 ；若长期储存该产品时，温度不应超过50 .产品每桶净重170kg。

生产厂家

香港奥莱斯特 (aowaseda) 石化有限公司

中国广东办事处地址：中国广东省江门市江海区东升路20号

联系人：黎国飞

手机：86 13902887300

电话：86 750-3807990

传真：86 750-3809993