

1	标称厚度		mm	0.15	0.18	0.20	0.23	0.25	0.30	0.35	0.40	0.45	
2	厚度极限偏差		mm	±0.02	±0.025	±0.03	±0.03	±0.03	±0.03	±0.035	±0.040	±0.045	
3	标称定量及 极限偏差		g/m ²	140 ± 20	190 ± 28	220 ± 33	260 ± 39	300 ± 45	350 ± 52	425 ± 63	500 ± 75	560 ± 84	
4	薄膜标称厚度		mm	0.05	0.075	0.10	0.125	0.15	0.19	0.25	0.30	0.35	
5	拉伸强度	纵向	不弯折	N/10 mm宽	80	120	140	180	190	270	320	340	370
			弯折后		80	105	120	150	170	200	300	320	350
		横向	不弯折		80	105	120	150	170	200	300	320	350
			弯折后		70	90	100	120	130	150	200	220	250
6	伸长率	纵向	不弯折	%	15				—		—		
			弯折后		10				5		3		
		横向	不弯折		20				—		—		
			弯折后		10				5		2		

7	击穿电压	KV	6	7	9	10	12	15	18	20	22
8	常态粘结性	—	不分层								
9	热态粘结性 (155 ± 2 10 min)	—	不分层、不起泡、不流胶								
10	温度指数		130								