

进口杜笙硼去除离子交换树脂

产品名称	进口杜笙硼去除离子交换树脂
公司名称	北京华豫清源国际贸易有限公司
价格	.00/升
规格参数	
公司地址	北京市丰台区花乡造甲村南里1号楼105室
联系电话	86-01052456750 13269232873

产品详情

杜笙ch-99

iso-9001/iso-14001/ohsas-18000

硼选择吸附树脂

ch-99 是一款去除水溶液中硼及其盐的选择性离子交换树脂。在一些化工工业以及农业用水中，微量的硼或者硼盐都可能是严重的问题。此种树脂可以在较大的ph范围内甚至有其他离子存在的溶液中有有效的去除硼以及硼盐，并且具有更高的数量级。

典型特性 (typical characteristics) : tulsion ch-99

主体结构/matrix structure 交联聚苯乙烯/cross linked polystyrene

物理型式/physical form 含水球状/wet spherical beads

官能团/functional group 胺聚羟基/poly hydroxy amine

离子型式/ionic form as shipped 氯/chloride

总交换量/total exchange capacity(meq/ml) 0.8 meq/ml

目数/screen size uss (湿) 16 to 50

粒度/particle size(95% minm.) 0.3 - 1.2 mm

平衡硼量/equilibrium boron capacity(meq/ml) 5.7 meq/ml

湿度/moisture content $46 \pm 3\%$

容积密度/bulk

density 680 - 720

gm/lit(43 - 47 lbs/cft)

最大温度/maximum thermal stability 80 (175

测试 (testing) :

tulsion ch-99

离子交换树脂的抽样和测试是按标准的测试程序，即astmd - 2187和is - 7330，1998.

包装 (packing) :

tulsion ch-99

super sack

1000 lit

super sack

ms drums

180 lit.

ms drums

hdpe lines bags

25lit.

hdpe lines bags

for handling, safety and storage requirements please refer to the individual material safety data sheets available at our offices. the data included herein are based on test information obtained by thermax limited. these data are believed to be reliable, but do not imply any warranty or performance guarantee. tolerances for characteristics are per bis/astm. we recommend that the user should determine the performance of the product by testing on his own processing equipment.

for further information, please contact: :