

# TPEE 5555HS DuPont property

产品名称	TPEE 5555HS DuPont property
公司名称	雄达（东莞）塑胶原料有限公司
价格	面议
规格参数	
公司地址	东莞市樟木头镇塑胶原料市场
联系电话	0769-18028910979 13649804300

## 产品详情

供应TPEE 5555HS DuPont property data

No this raw material description      material description

raw technical data Performance of projects to test conditions [state] test method of test data data units 24-hour water absorption of the basic performance --- ASTM D-570 0.7% The Taber-volume of the physical properties of CS-17 wheel ASTM D-1044 - mg/1000rev The proportion --- ASTM D-792 1.20 --- Melt flow rate --- ASTM D-1238 8.5 g/10min Heat distortion temperature @ 0.5Mpa ASTM D-648 90 The Taber-volume H 18 rounds ASTM D-1044 112 mg/1000rev Durometer hardness mechanical properties --- ASTM D-2240 55 --- Pliability modulus of 23 ASTM D-790 207 Mpa Tensile force --- ASTM D-638 40 Mpa Elongation at break --- ASTM D-638 500% Tensile force at 5% elongation 10% elongation --- ASTM D-638 ASTM D-638 6.9 10.3 Mpa Mpa The Ezo impact strength 23 ASTM D-256 J / m is not broken Initial tear resistance --- ASTM D-1004 158 kn / m Vicat softening point of thermal properties --- ASTM D-1525 180 Melting point --- ASTM D-3418 203 Heat distortion temperature @ 0.18Mpa ASTM D-648 49 The other sexual ability rubbing the curved incision growth performance --- ASTM D-1052> 1 × 105 ---