

产品详情

31.8	1.1/4	31.4	33.4	42.4	44.0	46.3	48.7	17.5	35.0	70.0	460	2.80
38.1	1.5	37.7	39.7	48.7	50.3	52.3	54.7	14.0	28.0	56.0	560	3.40
结构 胶管由内胶层、补强布、四层钢丝缠绕层和外胶层组成。应用适于输送液压流体如醇、液压油、燃油、润滑油、乳化液、烃等等。												
50.8	2	50.4	52.4	62.2	63.8	65.8	68.2	14.0	28.0	56.0	710	4.25
名义直径 nominal diameter		内径 inside diameter mm		钢丝层直径 reinforcement diameter mm		外径 outside diameter mm		工作压力 working pressure mpa	试验压力 proof pressure mpa	爆破压力 burst pressure mpa	最小弯曲半径 min.bend radius mm	参考重量 weight kg/m
mm	inch	min	max	min	max	min	max	max		min		
6.4	1/4	6.2	7.0	14.2	15.2	17.2	18.4	50.0	100.0	200.0	120	0.64
9.5	3/8	9.3	10.1	16.9	18.0	20.6	22.2	31.5	63.0	126.0	130	0.75
12.7	1/2	12.3	13.5	20.3	21.2	23.8	25.4	28.0	56.0	112.0	180	0.89
19.0	3/4	18.6	19.8	27.4	28.8	31.2	32.8	21.0	42.0	84.0	280	1.50
25.4	1	25.0	26.4	34.8	35.8	38.5	40.9	21.0	42.0	84.0	355	2.00