

## 特种合金--硼合金 硼合金

产品名称	特种合金--硼合金 硼合金
公司名称	莱芜市金石粉末冶金有限公司
价格	.00/个
规格参数	材质:硼合金 产地:山东莱芜 粒度:5--10目
公司地址	钢城区辛庄镇西照林村
联系电话	06345607166

## 产品详情

材质                      硼合金                      产地                      山东莱芜  
粒度                      5--10目

本公司生产供应硼合金，牌号及化学成份如下：

st-crb15 (a) (铬硼15a)

b13.5-16.5%,fe0.40%max, si0.50%max,al0.50%max,cu0.04%max,  
c0.03%max, s0.02% max ,p0.01%max,pb0.0005%max,,sn0.001%max,  
sb0.001%max,bi0.001%max, as0.0011%max,crbalance

st-crb15(b) (铬硼15b)

b13.5-16.5%, fe0.40%max,si0.50%max,al1.5%max,cu0.04%max,  
c0.03%max,s0.02%max,p0.01%max,pb0.0005%max,sn0.001%max,  
sb0.001%max,bi0.001%max,as0.001%max,crbalance

st-crb20(a)(铬硼20a)

b17.5-21.5%,fe0.4%max, si0.50%max, al0.5%max, cu0.04%max,  
c0.03%max, s0.02%max,p0.01%max,pb0.0005%max, sn0.001%max,

sb0.001%max, bi0.001%max, as0.001%max, crbalance

st-crb20(b) (铬硼20b)

b17.5-21.5%, fe0.40%max, si0.50%max, al1.5%max, cu0.04%max,  
c0.03%max, s0.02%max, p0.01%max, sn0.001%max, sb0.001%max,  
bi0.001%max, as0.001%max, crbalance

st-nib15(a) (镍硼15a)

b13.5-16.5%, co0.15%max, c0.02%max, al0.5%max, si0.50max,  
s0.02%max, p0.01max, fe0.30%max, cu0.035%max, zn0.03%max,  
pb0.001%max, sn0.001%max, sb0.001%max, bi0.001%max, nibalance

st-nib15(b) (镍硼15b)

b13.5-16.5%, co0.15%max, c0.02%max, al1.5%max, si0.50%max,  
s0.02%max, p0.01%max, fe0.30%max, cu0.035%max, zn0.03%max,  
pb0.001%max, sn0.001%max, sb0.001%max, bi0.001%max, nibalance

st-nib20(a) (镍硼20a)

b17.5-21.5%, co0.15%max, c0.02%max, al0.5%max, si0.50%max,  
s0.02%max, p0.01%max, fe0.30%max, cu0.035%max, zn0.03%max,  
pb0.001%max, sn0.001%max, sb0.001%max, bi0.001%max, nibalance

st-nib20(b) (镍硼20b)

b17.5-21.5%, co0.15%max, c0.02%max, al1.5%max, si0.50%max,  
s0.02%max, p0.01%max, fe0.30%max, cu0.035%max, zn0.03%max,  
pb0.001%max, sn0.001%max, sb0.001%max, bi0.001%max, nibalance

st-crnib15(a) (铬镍硼15a)

b13.5-16,5%, fe0.40%max, si0.50%max, al0.8%max, cu0.04%max,  
c0.03%max, s0.02%max, p0.01%max, pb0.0005%max, sn0.001%max,  
sb0.001%max, bi0.001%max, as0.001%max, cr39-43%, ni39-43%.

st-crnib15(b) (铬镍硼15b)

b13.5-16.5%,fe0.40%max,si0.50%max,al1.5%max,cu0.04%max,  
c0.03%max,s0.02%max,p0.01%max,pb0.0005%max, sn0.001%max,  
sb0.001%max,bi0.001%max,as0.001%max,cr39-43%,ni39-43%.

jst-cuti40b15(铜钛40硼15)

b13.5-16.5%,ti38-42%,fe0.50%max,si0.50%max, al1.0%max,  
c0.03%max,s0.02%max,p0.010%max,pb0.0005%max, sn0.001%max,  
sb0.001%max,bi0.001%max,as0.0010%max,cubalance.

jst-cuti20b10(铜钛20硼10)

b8.5-11.5%,ti18-22%,fe0.50%max, si0.50%max,al1.0%max,  
c0.03%max,s0.02%max, p0.010%max,pb0.0005%max,sn0.001%max,  
sb0.001%max,bi0.001%max,as0.0010%max,cubalance.

jst-tib20al25 (铜硼20铝25)

b17.5-21.5%, fe0.50%max,si0.50%max, al23-27%,c0.03%max,  
s0.02%max,p0.010%max, pb0.0005%max,sn0.001%max,sb0.001%max,  
bi0.001%max,as0.0010%max,ti balance.

jst-tib20al10 (铜硼20铝10)

b17.5-21.5%,fe0.50%max,si0.50%max, al8.5-11.5%, c0.03%max,  
s0.02%max, p0.010%max,pb0.0005%max,sn0.001%max, sb0.001%max,  
bi0.001%max,as0.0010%max,tibalance.

jst-tib30 (钛硼30)

b27-32%,fe0.60%max, si0.50%max,c0.03%max, mn0.01%max,  
s0.03%max,p0.03%max,al1.0%max, tibalance.

jst-mob10 (钼硼10)

b9-11%, fe0.40%max ,si 0.50%max , al0.80%max ,ni0.010%max ,  
s0.030%max ,p0.03%max , mobalance

jst-nbb10 (铌硼10)

b9-11% ,fe0.40% ,si0.50%max ,al0.80%max ,ni0.010%max ,  
s0.030%max .p0.03%max,nbbalance.

st-cob15(a) ( 钴硼15a )

b13.5-16.5% , ni0.15%max ,c0.02%max,al0.5%max, bsi 0.50max.  
s0.02%max,p0.01%max,fe0.30%max,cu0.035%max,zn0.03%max,  
pb0.001%max,sn0.001max,sb0.001%max, bi0.001%max,cobalance.

jst-cob15(b) ( 钴硼15b )

b13.5-16.5% , ni0.15%max ,c0.02%max, al1.5%max,bsi 0.50max.  
s0.02%max,p0.01%max,fe0.30%max,cu0.035%max, zn0.03%max,  
pb0.001%max,sn0.001max,sb0.001%max, bi0.001%max,cobalance.

st-cob20(a) ( 钴硼20a )

b17.5-21.5% , ni0.15%max ,c0.02%max, al0.5%max,bsi 0.50max.  
s0.02%max,p0.01%max,fe0.30%max,cu0.035%max,zn0.03%max,  
pb0.001%max,sn0.001max,sb0.001%max,bi0.001%max,cobalance.

st-cob20(b) ( 钴硼20b )

b17.5-21.5% , ni0.15%max ,c0.02%max,al1.5%max,bsi 0.50max.  
s0.02%max,p0.01%max,fe0.30%max,cu0.035%max, zn0.03%max,  
pb0.001%max,sn0.001max,sb0.001%max,bi0.001%max, cobalance.

st-cub2 (铜硼2)

cu97%min,b1.8-2.35%,al0.15%max, as0.01%max, fe0.15%max,  
mn0.03%max,p0.007%max,si0.10%max,pb0.020max,bi0.005%max,  
sb0.01max,se0.005%max,te0.005%max,杂质总和0.90%max

st-cub5(铜硼5)

cu93.5%min,b4-6%,al0.15%max, as0.01%max,fe0.15%max,  
mn0.03%max, p0.007%max,si0.10%max,pb0.020max,bi0.005%max,  
sb0.01max, se0.005%max,te0.005%max,杂质总和0.90%max

st-cub10 (铜硼10)

cu87.5%min,b8.5-11.5%,al0.15%max,as0.01%max,fe0.15%max,

mn0.03%max,p0.007%max,si0.10%max,pb0.02%max,bi0.005%max,

sb0.01%max,se0.005%max,te0.005%max,杂质总和0.90%max