

瑞典伊萨OK 50.40焊条E6013焊条

产品名称	瑞典伊萨OK 50.40焊条E6013焊条
公司名称	上海钰泰焊接材料有限公司
价格	20.00/公斤
规格参数	品牌:齐全 型号:OK 50.40
公司地址	上海市浦东新区川沙路500号205-248室
联系电话	021-31263590 13818577790

产品详情

镍基合金焊条

种类	esab 牌号	技术标准	熔敷金属力学性能		熔敷金属化学	
		sfa/aws	din 1736	屈服值mpa	抗拉强度m	
手工焊条	ok 92.05	a5.11 eni-1	el-niti3	320	450	
	ok 92.15	a5.11 enicrfe-2	el-nicr15fenb	420	660	
	ok 92.26	a5.11-90 enicrfe-3	el-nicr15femn	410	640	
	ok 92.45	a5.11 enicrmo-3	el-nicr20mo9 nb	480	800	
	ok 92.55	a5.11 enicrmo-6		460	705	
	ok 92.59		el-nicr22mo16	430		

不锈钢焊条

种类	esab牌号	技术标准		熔敷金属力学性能		
		sfa/aws	en	屈服值mpa	抗拉强度mpa	延伸率%
手工 焊条	ok 61.25	a5.4-9e308-15	en 1600e 19 9 h b 22	430	600	
	ok 61.30	a5.4 e308l-17	en 1600 e 19 9 l r 12	430	560	
	ok 61.35	a5.4 e308l-15	en1600e 19 9 l b 2 2	460	580	
	ok 61.41	a5.4 e308l-17	en1600 e 19 9 l r 5 3	420	560	
	ok 61.50	a5.4-92 e308h-17	en1600 e 19 9 h r 12	430	600	
	ok 61.80	a5.4-92 e347-17	en 1600e 19 9 n b r 12	500	630	
	ok 61.81	a5.4 e347-16	en1600 e 19 9 n b r 3 2	560	700	
	ok 61.85	a5.4 e347-15	en1600 e 19 9 n b b 2 2	500	620	
	ok 61.86	a5.4 e347-17	en1600 e 19 9 n b r 1 2	520	660	
	ok 63.20	a5.4 e316l-16	en1600 e 19 12 3 l r 1 1	480	580	
	ok 63.30	a5.4 e316l-17	en1600 e 19 12 3 l r 1 2	460	570	
	ok 63.31	a5.4 e316l-17	en1600 e 19 12 3 l r 3 2	460	570	
	ok 63.34	a5.4 e316l-16	en1600 e 19 12 3 l r 1 1	440	600	
	ok 63.35	a5.4 e316l-15	en1600e 19 12 3 l b 2 2	460	600	
	ok 63.41	a5.4 e316l-17	en1600 e 19 12 3 l r 5 3	430	570	
	ok 63.80	a5.4 e318-17	en 1600e 19 12 3 n b r 3 2	500	620	
	ok 64.30	a5.4 e317l-17	en1600 e 19 13 4 l r 3 2	480	600	

ok 67.13	a5.4 e310-16	en 1600 e 25 20 r 12	560	600		
ok 67.15	a5.4 e310-15	en 1600 e 25 20 b 22	410	590		
ok 67.20	a5.4 e309mol-16	en1600 e 23 12 2 l r 1 1	480	640		
ok 67.50	a5.4 e2209-17	en 1600e 22 9 3 n l r 3 2	660	820		
ok 67.55	a5.4 e2209-15	en 1600e 22 9 3 n l b 2 2	650	800		
ok 67.60	a5.4 e309l-17	en 1600e 23 12 l r 3 2	470	580		
ok 67.62	a5.4 e309-26	en1600 e 23 12 r 7 3	450	570		
ok 67.66	a5.4 e309l-16	en1600 e 23 23 l r 3 2	430	580		
ok 67.70	a5.4 e309mol-17	en1600 e 23 12 2 l r 3 2	510	620		
ok 67.75	a5.4 e309l-15	en1600 e 23 12 l b 4 2	460	570		
ok 68.15	a5.4 e410-15	en1600 e 13 b 4 2	390	520		
ok 68.17	a5.4 e410nimo-16	en 1600e 13 4 r 3 2	650	870		
ok 68.25	a5.4e410nimo-15	en 1600e 13 4 b 4 2	680	880		
ok 68.60		en 1600 e 25 4 r 3 2	660	800		
ok 68.81	a5.4 e312-17	en1600 e 29 9 r 3 2	580	750		
ok 69.25		en 1600e 20 16 3 mn l b 4 2	450	650		
ok 69.33	a5.4e385-16	en 1600e 20 25 5 cu n l r 3 2	400	575		

低合金钢焊条

种类	esab 牌号	技术标准		熔敷金属力学性能		
		sfa/aws	en	屈服值mpa	抗拉强度mpa	延伸率%
手工 焊条	ok 48.08	a5.5-96 e7018-g	en 499 e 46 5 1 ni b 32 h5	540	600	
	ok 73.15	a5.5 e7018-g	en 499 e 46 5 mn 1ni b 42 h5	550	610	
	ok 73.68	a5.5 e8018-c1	en 499 e 46 6 2ni b 32 h5	520	610	
	ok 73.79	a5.5 e8016-c2	en 499 e 46 6 3ni b 12	520	610	
	ok 74.46	a5.5 e7018-a1	en 1599 e mo b 42	460	560	
	ok 74.70	a5.5 e8018-g	en 499 e 46 mnmo b 32	540	630	
	ok 74.78	a5.5 e9018-d1	en 1599 e mo b42	600	650	
	ok 75.75	a5.5 e11018-g	en 757 e 69 5 mn2 nicrmob 42 h5	755	820	
	ok 75.78		en757 e89 6 mn3nicrmo b 42 h5	920	965	
	ok 76.18	a5.5 e8018-b2	en 1599 e crmo 1 b 42 h5	530	620	
	ok 76.28	a5.5 e9018-b3	en 1599 e crmo 2 b 42 h5	550	650	
	ok76.35	a5.5 e8015-b6	en 1599 e crmo 5 b 32 h5	/	460	
	ok 76.96	a5.5 e8015-b8	en 1599 e crmo 9 b	/	> 450	