

		nos/dia.	al	steel	total			
20.3%iacs	35	7/2.50	8.59	25.77	34.36	7.50	2.4927	
	45	7/2.90	11.56	34.68	46.24	8.70	1.8522	
	50	7/3.00	12.37	37.11	49.48	9.00	1.7310	
	55	7/3.20	14.08	42.22	56.30	9.60	1.5213	
	65	7/3.50	16.84	50.51	67.35	10.50	1.2717	
	70	7/3.60	17.81	53.44	71.25	10.80	1.2021	
	80	7/3.80	19.85	59.54	79.39	11.40	1.0788	
	95	7/4.16	23.79	71.35	95.14	12.48	0.9002	
	100	19/2.60	25.22	75.66	100.88	13.00	0.8524	
	120	19/2.85	30.30	90.91	121.21	14.25	0.7094	
	150	19/3.15	37.02	111.05	148.07	15.75	0.5807	
	185	19/3.50	45.70	137.10	182.80	17.50	0.4704	
	210	19/3.75	52.46	157.39	209.85	18.75	0.4098	
	240	19/4.00	59.69	179.07	238.76	20.00	0.3601	
	300	37/3.20	74.39	223.18	297.57	22.40	0.2907	
	380	37/3.60	94.16	282.46	376.62	25.20	0.2297	
	420	37/3.80	104.91	314.71	419.62	26.60	0.2061	
	465	37/4.00	116.24	348.72	464.96	28.00	0.1860	
510	37/4.20	128.15	384.46	512.61	29.40	0.1687		