

RUBBER ACCELERATOR ZMBT

产品名称	RUBBER ACCELERATOR ZMBT
公司名称	河南巨锦进出口贸易有限公司
价格	面议
规格参数	
公司地址	郑州市金水区经七路21号华凯大厦6028室（注册地址）
联系电话	86-371-63210302 13140139577

产品详情

rubber accelerator zmbt(mz)

chemical name:zinc 2-mercaptobenzothiazole molecular formula:c14h8n2s4zn cas no:155-04-4 specification:

item	mz(low m+)			mz(high m+)		
	powder	oiled powder	granule	powder	oiled powder	granule
appearance (visual inspection)	light yellow powder (granule)			light yellow powder (granule)		
initial m.p. oc	200.0	200.0	200.0	200.0	200.0	200.0
heating loss %	0.40	0.40	0.40	0.40	0.40	0.40

zinc content %	20.0-25.0	20.0-25.0	20.0-25.0	15.0-18.0	15.0-18.0	15.0-18.0
free m %	0.0-2.0	0.0-2.0	0.0-2.0	14.0-18.0	14.0-18.0	14.0-18.0
residues on sieve(150 μ m), %	0.10	0.10	\	0.10	0.10	\
residues on sieve(63 μ m), %	0.40	0.40	\	0.40	0.40	\
oil content, %	\	1.0-2.0	\	\	1.0-2.0	\
granule diameter, mm	\	\	1.5-2.5	\	\	1.5-2.5

properties:light yellow powder (granule) with a little bitter, no poison. the density is 1.70(20oc), the decomposable temperature is 300oc. soluble in chloroform, acetone, partly soluble in benzene, ethanol, ccl4, insoluble in gasoline, water and ethyl acetate. decomposition when meeting strong acid and strong alkali. application:zmbt is mainly used together with zdmc and zdec as primary accelerator for latex; can achieve higher modulus of valcanized latex. in addition, it can achieve good compressive deformation resistance without additional curing time. zmbt will not affect the stability of latex. packing:25kg plastic woven bag, paper with plastic film bag, kraft paper bag, or jumbo bag. storage:the product should be stored in the dry and cooling place with good ventilation, avoiding exposure of the packaged product to direct sunlight. the validity is 2 years .