



												o不锈钢，抗热裂纹性能优良。
CHG-316 L6	ER316L	H00Cr19Ni12Mo2	0.020	1.88	0.38	19.23	12.30	Mo2.36	530	43		超低碳型，较CHG-316、CHG-316耐腐蚀性更好。
CHG-317	ER317	H00Cr20Ni14Mo3	0.04	1.86	0.46	19.3	14.2	Mo3.5	596	42		适于焊接硫酸、亚硫酸及其盐腐蚀的容器。
CHG-347	ER347	H0Cr20Ni10Nb	0.06	1.84	0.41	19.4	9.5	Mo0.89	630	40		焊接含Nb不锈钢、抗晶间腐蚀和耐热性好。
CHG-410	ER410	H1Cr13	0.10	0.47	0.42	11.80	0.20	-	510	26		适于焊接Cr13不锈钢
CHG53	ER70S-3	ER50-3	0.09	1.25	0.49	S0.016	S0.013		570	29		低碳钢及50kg级高强钢的焊接
CHG56	E70S-6	ER50-6	0.08	1.54	0.89	S0.012	S0.011		540	28		低碳钢及50kg级高强钢的焊接
CHG52T	ER70S-G	ER50-G	0.08	1.52	0.82	S0.009	S0.011		585	29		低碳钢及50kg级高强钢的焊接