

2	厚度允 差	mm	± 0.02	± 0.02	± 0.02	± 0.02	± 0.03	± 0.03	± 0.03	± 0.03	± 0.03
	Thicknes sallowed toleran ce										
3	标称定 量	g/m2	120	138	155	180	210	255	300	450	550
	Nominal gramm age										
5	薄膜标 称厚度	um	30	30	30	30	30	30	30	30	30
	Film n ominal thickness										
6	拉伸强 度(纵向)	N/10mm	100	100	100	110	120	120	200	200	200
	Tensile strength (MD)										
7	拉伸强 度(横向)	N/10mm	70	70	70	75	80	95	105	105	105
	Tensile strength (XD)										
8	伸长率 (纵向)	%	2	2	2	2	2	2	2	2	2
	Elongatio n (MD)										
9	伸长率 (横向)	%	8	8	8	8	8	8	8	8	8
	Elongatio n (XD)										
10	击穿电	KV	3.5	3.5	3.5	3.5	3.5	4.5	5	5	5

压

Electric
breakd
own vo
ltage

11 热态粘 不分层、不起泡、不流胶
结120 ±
2 10 No delamination,no blister,no adhesive flow
Min

Bond st
rength
at 180
± 2