

移印免烘烤不锈钢油墨

| | |
|------|------------------------------|
| 产品名称 | 移印免烘烤不锈钢油墨 |
| 公司名称 | 上海凯贤油墨科技有限公司 |
| 价格 | 180.00/公斤 |
| 规格参数 | 品牌:欧莱斯 型号:MPE 产地:德国 |
| 公司地址 | 上海市嘉定沪宜公路6106号 |
| 联系电话 | 021-59507952-103 18201845192 |

产品详情

【性能检测】1、3M胶带划百格测试：100%无脱落2、耐冲压测试：1mm厚铝板180°折弯无变化。3、耐酒精测试：用脱脂棉沾浓度99%工业酒精以500G力水平来回200次无脱色。【注意事项】1、先少量试印确认符合要求后再批量生产。2、做好承印物的表面清除油脂及杂质工作，以促进附着效果。3、附着力、硬度、耐酸性、耐酒精性、耐化学品性、抗划伤性、耐磨性等性能的检测，需要完全固化后方可检测。4、未经允许情况下，不得将本系列油墨与其它类型油墨混用及配色。5、油墨，稀释剂使用及储存时严禁烟火。6、使用时注意施工场所的通风状况良好，尽量避免**直接接触。7、本品不慎溅入口、鼻、眼、耳内，应用大量水清洗或直接求助医生。8、技术参考数见下表：检验项目 检验结果

| | | | | | | | | | | | |
|-----------|----------|--|---------|-----------|----------|------------------|------|-----------|--------|-----|-----|
| 测试条件 | 油墨线度 | 12um | 刮板细度 | 计干膜光泽 | 65° | 60° | 镜面光泽 | 计干燥速度 | 表干 | | |
| 25 | ×5-10min | 或60 | ×2-3min | 实干 | 25 | 12Hr | 或60 | ×10min | 耐酒精性 | 无变化 | |
| 500克力/cm2 | 酒精棉 | 200次 | 来回 | 附着力 | 100/100 | 1mm × 1mm × 100格 | 3M胶纸 | 剥离 | 耐酸性 | 无变化 | |
| 浸泡5% HCl | × 24Hr | 耐碱性 | 无变化 | 浸泡5% NaOH | × 24Hr | 耐盐性 | 无变化 | 浸泡5% NaCl | × 24Hr | 耐水性 | 无变化 |
| 浸泡20 | 自来水 | × 96Hr | 耐磨性 | 不见底 | 500克/cm2 | 负载含砂 | 橡皮 | 200来回 | 耐热性 | 无变化 | |
| 80 | × 12Hr | The products are mainly used in screen printing and the printing of various kinds of metal, glass, vacuum plating, electroplating, electrophoresis, water anodic alumina, electrolytic plate, aluminum plate, plastic spraying, dusting, electrostatic spray painting, paint surface and various ceiling oxide board, mirror panels, coated board, roller coated board and other products.2, product characteristics: light, good adhesion, fast drying, stamping resistance.3, diluent: with our B-03 special thinner or 783 open oil, washing network water cleaning screen with 718.4, curing agent: one component use, can also choose to add our JS-10 special curing agent is used to increase the ink adhesion and physical and chemical resistance.5, printing ink allocation methods: open cans to stir well, take appropriate amount needed to dilute ink printing viscosity. If you need to add curing agent, first add curing agent after mixing and set aside for 10 minutes, and curing agent for ink completely crosslinking after dilution.6, the drying time: dry, dry time table for 5-10 minutes, work time within 24 hours, 80 degrees bake for 20 minutes can be dried quickly.7, adding curing agent after the use of time: 4-6 hours, expired please abandoned, residual ink Unrecyclable.[detection] performance1, 3M tape row adhesion test: 100% without shedding2, stamping resistance test: 1mm thick aluminum 180 degree bend without change.3, alcohol resistant test: with cotton dipped in 99% alcohol concentration of industry to 500G stress level and back 200 times without decolorization.[note]1, the first small try printing again after confirmation of compliance with the requirements of mass production.2, do a good job in the substrate surface to | | | | | | | | | |

remove grease and impurities, in order to promote the adhesion effect. Detection of 3, adhesion, hardness, acid resistance, alcohol resistance, chemical resistance, scratch resistance, abrasion resistance and other properties, Fully cured before detection. 4, without permission, may not use the series of ink and other types of ink mixing and matching. 5, ink, fireworks is strictly prohibited the use of thinner and storage. 6, the use of ventilation conditions attention the construction site is good, try to avoid direct contact with skin. 7, this product is inadvertently splashed entrance, nose, eyes, ears, use a large number of water washing or direct help doctor.