

聚乙烯移印油墨专用聚乙烯移印油墨

产品名称	聚乙烯移印油墨专用聚乙烯移印油墨
公司名称	上海凯贤印刷科技有限公司
价格	180.00/公斤
规格参数	品牌:OLS 型号:400a 产地:德国
公司地址	上海市嘉定区外冈西冈身路777号
联系电话	021-59507952 18074309897

产品详情

聚乙烯移印油墨

特性：拥有和德国彩丽宝一样的颜色，主要用于PP、PE、BOPP等材料上，具有高色泽、高色彩、高遮盖力、高稳定性、耐酒精及耐磨擦之特点。印刷：丝印移印均可。

表干及实干时间：表干时间自然挥发5-10分钟；实干时间在24小时以内。

稀释及清洗：SV3慢干开油水、UVK1（移印开油水）同时可使用718洗网水清洗。

测试方法（完全干燥后）：

1、3m胶纸粘在画有百格的油墨表面，45度角迅速拉起不脱油； 2、纯度99%的工业酒精，一千克砝码用棉布包住在油墨表面，以水平力来回拉200次无脱色；

3、耐磨：橡皮擦500g力水平来回擦500次。 使用方法：

1、使用前应充分搅拌，用后随时封闭；

2、搅拌时加开油水10-15%，稀释到印刷粘度； 3、网板塞网时可用洗网水清洗；

4、不得与其它类型油墨混合使用。 注意事项： 1、塑胶材料的外观相似，但可能会是不同的材料，客户需试印确定其符合要求后，再批量印刷；

2、在移印过程中，如出现拉丝或散开，可适当加入一些慢干膏即可；

3、环境温度过高，将会影响油墨原有质量；

4、根据气候变化，请远离火源，阴暗环境下存放。

5、技术参考数见下表： 检验项目 检验结果 测试条件

油墨线度 12um 刮板细度计 干膜光泽 65°

60° 镜面光泽计 干燥速度 表干 25 × 5-10min

或60 × 2-3min 实干 25 12Hr或60 × 10min 耐酒精性

无变化 500克力/cm²酒精棉200次来回 附着力 100/100

1mm × 1mm × 100格3M胶纸剥离 耐酸性 无变化

浸泡5%HCl × 24Hr 耐碱性 无变化 浸泡5%NaOH × 24Hr

耐盐性 无变化 浸泡5%NaCl × 24Hr 耐水性 无变化
浸泡20 自来水 × 96Hr 耐磨性 不见底
500克/cm²负载含砂橡皮200来回 耐热性 无变化 80 × 12Hr

Ink characteristics: have and Germany Caili treasure the same color, is mainly used for PP, PE, BOPP and other materials, with a high color, high color, high covering power, alcohol resistant and wear resistance, high stability. Printing: silk screen printing can be. Table dry and work time: surface dry time natural volatile 5-10 minutes; work time within 24 hours. Dilution and cleaning: SV3 slow dry open water, UVK1 (printing open water) also can use 718 washing network water cleaning. Test method (completely dry): 1, 3M adhesive tape sticky ink surface adhesion in painting, 45 degree angle quickly pulled off the oil; 2, purity 99% of industrial alcohol, using cotton bag in the surface of the ink one kilogram weight to horizontal force and pull 200 times without decolorization; 3, wear: the eraser 500g force level wipe 500 times back and forth. Method of use: 1, before the use should be fully mixing, use at any time after the closure; 2, mixing an additional 10-15% in oil and water, diluted to printing viscosity; 3, mesh plug mesh can be used when washing network water cleaning; 4, shall not be mixed with other ty [PES](#) of ink. The matters needing attention: 1, the plastic material of similar appearance, but may be of different materials, customers need to try to determine its requirements, and then bulk printing; 2, in the printing process, such as drawing or spread out, may be appropriate to add some slow dry paste can be; 3, the ambient temperature is too high, it will affect the quality of the original ink; 4, according to the climate change, please stay away from fire, stored in dark environment.