单组份自干金属油墨

产品名称	单组份自干金属油墨
公司名称	上海凯贤印刷科技有限公司
价格	180.00/公斤
规格参数	品牌:OLS 型号:A60 产地:德国
公司地址	上海市嘉定区外冈西冈身路777号
联系电话	021-59507952 18074309897

产品详情

油墨特性:1、平光、附着力佳、耐汽油、耐化学品;2、手感好,流平性佳、面光洁;3、表面硬度好,耐冲击性能强、抗刮伤;4、耐汽油、耐酒精、耐化学品程度佳;印刷:选用网目为100-350目,以120T网纱计算涂覆盖面积每公斤达30~35㎡。表干时间自然挥发5-15分钟,实干时间在24小时以内,48小时后达优秀性能。

- 1.用配套专用稀释剂开油水2.用718洗网水洗网。
- 3. 或添加配套硬化剂10%可增加附着力,提高墨膜硬度。 4. 烤箱80 烘烤10分钟佳能更优。
- 测试方法(完全干燥后):1.3M胶纸粘在画有百格的油墨表面45度角迅速拉起不脱油。使用方法:1.建议用我公司专用稀释剂进行稀释,不建议使用783慢干稀释剂稀释,使用前应充分搅拌,用后随时密封。2.搅拌时加本公司配套开油水10-12%,稀释到印刷适合粘度,移印稀释使用移印专用稀释剂;用7.18洗网水清洗。3.不得与其它类型油墨混合使用,否则容易出现其他附着力,化学反应等不良现象。
- 4. 加入固化剂的油墨使用时限为8小时,过期请弃用,剩余油墨不可回收注意事项:
- 1. 各种承印物料的外观相似,但可能会是不同的材料,客户需先试印,确其符合要求后,再批量生产。
- 2.在移印过程中,如出现拉丝或散开,可适当加入一些慢干膏即可;3.环境温度过高,将会影响油墨原有质量。白色超越150都会变色,烘烤时请用木质材料垫底进行烘烤,不得直接接触铁
- 4. 根据气候变化,请远离火源,阴暗处15度-30度环境下存放

Brand: but MY name: anodic oxidation INK Numbers: 65496 Anodic oxidation ink series The product is produced with advanced import acrylic resin and senior pigment after fine grinding system, used in combination to ABS, PP, PET, all kinds of metal, glass, cerami c, stone, electroplating (water cut electroplating), anodic alumina surface and roast (spray pai nt products of screen and pad printing, not needing curing agent, and does not need to bake, can obtain excellent adhesion. Ink characteristics: 1 the classification includs glass, a dhesion, good resistance to gasoline, alcohol, resistance to chemicals;

- 2, feel is good, flow ping sex, good surface is bright and clean;
- 3 and fine surface hardness, impact resistance properties of strong, resistance to scratch;
- 4, resistant to gasoline, alcohol, resistant to chemicals resistant degree good; Printing: Choos e for 100-350 mesh mesh to 120 T nets yarn with coverage area calculation per kilogram of 30 to 35 m². Dry time table natural volatilize 5 to 15 minutes, action in time wi

thin 24 hours, after 48 hours of optimum performance.

- 1. With matching special thinner, open oil and water
- 2. Wash washing nets with 718 net.
- 3. Or add hardener 10% supporting can increase adhesion, improve ink film hardness.
- 4. Preheat the oven to 80 bake for 10 minutes Canon even better.

Test method (dry): 1.3 M tape stuck in the picture has's ink surface 45 degree Angle quickly pull up not to take off oil. 2. The purity of 99% alcohol 500 G force in ink surface wipe 300 times back and forth without decoloring. Method of use: 1. The p roposal with my company special thinner to dilute, not recommended dry thinners diluted 783 slow, before the use should be fully mixing, use at any time after sealing. 2. Add the company supporting stirring open 10 to 12%, oil and water dilute the printing for viscosity, pad printing dilution use moving printing special thinner,; Use clean water to w ash the nets 718.