

901型钢丝编织液压橡胶软管

| | |
|------|--------------------------|
| 产品名称 | 901型钢丝编织液压橡胶软管 |
| 公司名称 | 陕西延长石油西北橡胶有限责任公司 |
| 价格 | .00/个 |
| 规格参数 | |
| 公司地址 | 咸阳市秦都区西华路一号院内 |
| 联系电话 | 029-33622642 18149022885 |

产品详情

Standard:

Q/XXC016-2005

Specifications:

One Layer of Wire Braided Reinforcement

Size

I.D

W.D

O.D

W.P

P.P

B.P

B.R

W.T

In

Min

Max

Min

Max

Min

Max

MPa

MPa

MPa

mm

kg/m

3/16-1

4.0

4.5

9.5

10.5

0.8

1.5

40

50

100

90

0.27

1/4-1

5.8

6.5

11.1

12.1

14.2

15.4

32

40

80

100

0.35

5/16-1

7.8

8.5

13.1

14.1

16.2

17.4

28

35

70

115

0.43

3/8-1

9.8

10.5

15.1

16.1

18.1

19.3

25.6

32

64

130

0.49

1/2-1

12.8

13.5

18.9

19.9

21.9

23.1

22.4

33.6

56

180

0.64

5/8-1

15.8

16.6

22.0

23.0

24.7

26.3

16.8

21

42

205

0.75

3/4-1

18.8

19.8

25.0

26.0

27.6

29.2

14.4

18

36

240

0.84

7/8-1

21.8

22.8

28.0

29.0

30.6

32.2

12.8

16

32

280

1.00

1-1

24.8

25.8

31.5

32.5

34.2

35.8

11.2

14

28

300

1.10

1-1/4-1

31.6

33.6

38.5

39.5

41.8

44.2

9.0

11.5

22.5

420

1.40

1-1/2-1

37.7

39.8

45.5

46.0

48.8

51.2

7.0

9

17.5

500

1.58

1-3/4-1

44.6

45.6

52.5

53.0

54.8

57.2

5.0

8

12.5

550

1.80

2-1

50.7

52.0

57.7

58.8

62.3

64.7

3.0

6

7.5

630

1.99

Two Layers of Wire Braided Reinforcements

Size

I.D

W.D

O.D

W.P

P.P

B.P

B.R

W.T

In

Min

Max

Min

Max

Min

Max

MPa

MPa

MPa

mm

kg/m

1/4-2

5.8

6.5

12.9

13.9

16

17.2

56.0

70.0

140

100

0.48

5/16-2

7.8

8.5

14.9

15.9

18

19.2

48.0

60.0

120

115

0.60

3/8-2

9.8

10.5

16.9

17.9

19.9

21.1

40.0

50.0

100

130

0.68

1/2-2

12.8

13.5

20.7

21.7

23.7

24.9

36.0

45.0

90

180

0.93

5/8-2

15.8

16.6

23.7

24.7

26.5

28.1

32.0

40.0

80

205

1.07

3/4-2

18.8

19.8

26.7

27.7

29.4

31.0

25.0

31.5

63

240

1.08

7/8-2

21.8

22.8

30.7

31.0

32.6

34.0

22.0

27.5

55

280

1.28

1-2

24.8

25.8

33.5

34.5

36.0

37.6

21.0

26.5

52

300

1.52

1-1/4-2

31.6

33.6

40.2

41.2

43.8

46.2

17.0

21.5

42.5

420

1.91

1-1/2-2

37.7

39.8

46.5

47.5

49.8

52.2

12.0

15.0

30

500

2.10

1-3/4-1

44.6
45.6
53.5
54.5
56.8
59.2
9.0
13.5
22.5
550
2.40
2-2
50.7
52.0
59.5
60.5
62.8
65.2
8.0
12.0
20
630
2.51

Three Layers of Wire Braided Reinforcements

Size

I.D

W.D

O.D

W.P

P.P

B.P

B.R

W.T

In

Min

Max

Min

Max

Min

Max

MPa

MPa

MPa

mm

kg/m

5/16-3

7.8

8.5

16.5

17.5

19.6

20.8

50.0

75

125

115

0.79

3/8-3

9.8

10.5

18.5

19.5

21.5

22.7

45.0

62.5

112.5

130

0.90

1/2-3

12.8

13.5

22.5

23.5

25.5

26.7

40.0

56

100

180

1.20

5/8-3

15.8

16.6

25.5

26.5

28.3

29.9

35.0

43.5

87.5

205

1.39

3/4-3

18.8

19.8

28.5

29.5

31.2

32.8

28.0

35

70.5

240

1.54

7/8-3

21.8

22.8

31.5

32.5

34.2

35.8

25.0

31.5

62.5

280

1.66

1-3

24.8

25.8

34.6

35.6

37.2

38.8

24.0

30

60.5

300

1.97

1-1/4-3

31.6

33.6

42.0

43.0

45.8

48.2

19.0

24

47.5

420

2.48

1-1/2-3

37.7

39.8

48.0

49.0

51.8

54.2

15.0

19

37.5

500

2.90