ABS台湾台化（华东总代理商）

产品名称	ABS台湾台化（华东总代理商）
公司名称	上海达双贸易有限公司
价格	.00/KG
规格参数	ABS台湾台化:ABS台湾台化 齐全:齐全 台湾:台湾
公司地址	上海市奉贤区南桥环城西路2225号第二幢3186室（注册地址）
联系电话	13818401469

产品详情

ABS丙烯腈-丁二烯苯乙烯塑料

达双公司代理台湾台化

英文名称 Acrylonitrile Butadiene Styrene plastic

本公司长期供应阻燃防火ABS ,抗紫外线ABS,通用级高光泽度ABS,高耐热性ABS,汽车专用ABS,医用级ABS,挤出(挤塑)级ABS,吹塑级ABS,耐冲击级ABS,耐高温级ABS,透明级ABS，等等。

TAIRILAC AE8000 Formosa Chemicals & Fibre Corporation ABS

TIRILAC AE8200 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AF3500 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AF3535 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AF3600 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AF3800 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG1000 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG10A1 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG10AP Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG10NP Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG12A0 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG12A1 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG12A3 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG12AJ Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15A0 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15A1 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15A2 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15A3 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15AJ Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15E0 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15E1 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG15E3 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AG22AT Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AH2003 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC ANC100 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC ANC120 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC ANC200 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AP22AT Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AT5500 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AT5800 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AT5900 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AX4000 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AX4100 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AX4200 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AX4300 Formosa Chemicals & Fibre Corporation ABS

TAIRILAC AXT040 Formosa Chemicals & Fibre Corporation ABS

ABS 加工条件

ABS常用于镀金品，注意事项如下：1、料管温度宜高，约210~230度2、射出温度宜慢（用二次加压法）、射出压力宜低，否则合压力集中3、不可用离模剂4、以背压控制收缩下陷及熔接线之留痕5、成品表面不可有创痕加工温度：1、螺杆式套筒加热温度180~240度，射出压力700~1200kg/cm²,水分控制在0.3%以下才可成型，料管温度第一段为200-250度，第二段为190-240度，第三段为180-240度，第四段为160-200度，模具温度为40-85度，螺杆转速为40-100rpm，保压为20-50kg/cm²,背压为0-200 kg/cm²。2、柱射式套筒温度：喷嘴200-260度，第一段200-260度，第二段为200-240度，第三段为180-2630度，模温50-80度，射出压力1000-2000 kg/cm²。

ABS 的应用：

ABS树脂具有良好的综合性能，所以其应用相关广泛。ABS树脂广泛应用于汽车工业、电器仪表工业和机械工业中，常作齿轮、汽车配件、挡泥板、扶手、冰箱内衬、叶片、轴承、把手、管道、接头、仪表壳、仪表板、盘、安全帽等；在家用电器和家用电子设备的应用前景更广阔，如电视机、收录机、冰箱、冷柜、洗衣机、空调机、吸尘器和各种小家电器材；日用品有鞋、包、各种旅行箱、办公设备玩具及各种容器等；低发泡的ABS能代替木材，适合作建材、家具和家庭用品。电镀制品常作为金属代用品，如栅条、散热器、车轮罩等配件以及铭牌、装饰件等。

ABS 的特性：

ABS具有优良的综合物理和机械性能，极好的低温抗冲击性能、尺寸稳定性、电性能、耐磨性、抗老化药品性、染色性，成型加工和机械加工较好。ABS树脂耐水、无机盐、碱和酸类，溶于蜷、酮、酯。ABS树脂热变形温度较低，可燃，耐候性较差。熔融温度在217-237度，热分解温度在250度以上。黑色的颜料ABS制品耐候性较好，他在室外暴露2年经太阳和大气侵蚀，其外观和性能都基本不变。

本司供应通用塑胶：PP PE ABS EVA HIPS HDPE PVC 工程塑料：PA6 PA66 PBT PC PET PMMA POM PC/ABS PC/PBT 高性能塑料：PPS SPS PA46 PA6T PA12 PSU PES PEI LCP PEEK COC PPA PA9T 热塑弹性体：POE TPE TPR TPEE TPV TPX TPU SEBS SBS 热固性塑料：EPDM

可提供原厂物性表,加工参数，ROHS(SGS)环保产品认证书报告及UL认证,FDA认证,材质证明及物质安全资料表(MSDS)等产品证书,质量保证，价格优惠，如有需要敬请来电联系！我们将竭诚为你服务!

注：由于原料价格会变动，如需了解最新价格，请来电询价！不便之处，还请谅解！