

# 现货供应PA66 美国杜邦 70G30HSLR 尼龙66原料

产品名称	现货供应PA66 美国杜邦 70G30HSLR 尼龙66原料
公司名称	惠州市熙利塑化有限公司
价格	.00/KG
规格参数	PA66:3 PA66:3 美国:3
公司地址	惠州市
联系电话	18306228159

## 产品详情

品牌: 杜邦

型号: 70G30HSLR

特性: 热稳定/加纤30%增强级尼龙

PA66 Zytel 70G30HSLR NC010中英文物性参数物性表

以下是PA66 Zytel 70G30HSLR NC010中英文物性表

DuPont Zytel 70G30HSLR NC010 Nylon 66 ( PA66-聚酰胺-尼龙66 )

The property table is provided by [www.plasticres.com](http://www.plasticres.com), welcome to download, reprint please indicate the source!

Physical Properties物理性质

Metric公制数据

English英制数据

Comments测试方法

Density密度

1.37 g/cc

0.0495 lb/in

DAM; ISO 1183

Filler Content填料含量

30 %

30 %

DAM

Water Absorption吸水率

1.9 %@Temperature 23.0 ° C

1.9 %@Temperature 73.4 ° F

Equilibrium 50%RH; DAM; ISO 62, Similar to

6.0 %@Temperature 23.0 ° C

6.0 %@Temperature 73.4 ° F

Saturation, immersed; DAM; ISO 62, Similar to

Viscosity粘度

58000 cP@Shear Rate 7000 1/s, Temperature 305 ° C

58000 cP@Shear Rate 7000 1/s, Temperature 581 ° F

DAM; ISO 11443

196000 cP@Shear Rate 500 1/s, Temperature 305 ° C

196000 cP@Shear Rate 500 1/s, Temperature 581 ° F

299000 cP@Shear Rate 1000 1/s, Temperature 275 ° C

299000 cP@Shear Rate 1000 1/s, Temperature 527 ° F

350000 cP@Shear Rate 700 1/s, Temperature 275 ° C

350000 cP@Shear Rate 700 1/s, Temperature 527 ° F

404000 cP@Shear Rate 500 1/s, Temperature 275 ° C

404000 cP@Shear Rate 500 1/s, Temperature 527 ° F

Linear Mold Shrinkage, Flow线性收缩率/流动

0.0030 cm/cm@Thickness 2.00 mm

0.0030 in/in@Thickness 0.0787 in

Parallel; DAM; ISO 294-4

Linear Mold Shrinkage, Transverse线性收缩率/横向

0.011 cm/cm@Thickness 2.00 mm

0.011 in/in@Thickness 0.0787 in

Normal; DAM; ISO 294-4

Mechanical Properties力学性能

Tensile Strength at Break断裂拉伸强度

130 MPa@Temperature 23.0 ° C

18900 psi@Temperature 73.4 ° F

50%RH; ISO 527

195 MPa@Temperature 23.0 ° C

28300 psi@Temperature 73.4 ° F

DAM; ISO 527

Elongation at Break断裂伸长率

3.3 %@Temperature 23.0 ° C

3.3 %@Temperature 73.4 ° F

DAM; ISO 527

5.0 %@Temperature 23.0 ° C

5.0 %@Temperature 73.4 ° F

50%RH; ISO 527

Tensile Modulus拉伸模量

7.20 GPa@Temperature 23.0 ° C

1040 ksi@Temperature 73.4 ° F

## 店主留言:

因原料型号较多，价格行情变化快，网上报价和数量与实际行情和库存可能会出现差异，请先致电工作人员确认。莫小姐：15119093218（微信同号）我司专业现货供应ABS.EVA,TPU,PC.PA46,POM.PP.PE，PA 6/66等通用及工程塑胶原料，产品质量保证，原厂原包，价格合理,可提供专业的原料售后工程注塑技术服务。可提供相关产品详细物性表，SGS（RoHS）环保认证，UL黄卡，FDA食品认证，国税,一般纳税人公司，塑胶原料随石油价格的波动会发生涨跌。网上的价格为参考价格，具体的价格请以电话洽谈联系为准。