

美国杜邦POM 500P POM美国杜邦500P POM500P

产品名称	美国杜邦POM 500P POM美国杜邦500P POM500P
公司名称	东莞市奥亚塑胶原料有限公司
价格	.00/千克
规格参数	包装:原厂原包装袋 型号:500P 产地:美国
公司地址	总部位于香港，大陆公司位于广东省东莞市
联系电话	13794872977 18128015760

产品详情

Delrin500P NC010

ACETAL RESIN

杜邦高性能聚合物

产品说明：

中粘度 缩醛均聚物

良好的加工性能，

润滑，易脱模。

Physical Properties物理性质

Metric公制数据

English英制数据

Comments测试方法

Specific Gravity 密度

1.42 g/cc

ASTM D792

Water Absorption 吸水率

0.28 %@Temperature 23.0 ° C

0.28 %@Temperature 73.4 ° F

Equilibrium 50%RH; ASTM D570

0.30 %@Temperature 23.0 ° C

0.30 %@Temperature 73.4 ° F

Equilibrium 50%RH; ISO 62, Similar to

0.40 %@Temperature 23.0 ° C

0.40 %@Temperature 73.4 ° F

Immersion 24h; ASTM D570

0.60 %@Temperature 23.0 ° C

0.60 %@Temperature 73.4 ° F

Immersion 24h; ISO 62, Similar to

1.4 %@Temperature 23.0 ° C

1.4 %@Temperature 73.4 ° F

Saturation; ASTM D570

Saturation, immersed; ISO 62, Similar to

Viscosity 粘度

67000 cP@Shear Rate 7000 1/s, Temperature 230 ° C

67000 cP@Shear Rate 7000 1/s, Temperature 446 ° F

ISO 11443

73000 cP@Shear Rate 7000 1/s, Temperature 215 ° C

73000 cP@Shear Rate 7000 1/s, Temperature 419 ° F

179000 cP@Shear Rate 2000 1/s, Temperature 200 ° C

179000 cP@Shear Rate 2000 1/s, Temperature 392 ° F

193000 cP@Shear Rate 1000 1/s, Temperature 230 ° C

193000 cP@Shear Rate 1000 1/s, Temperature 446 ° F

219000 cP@Shear Rate 700 1/s, Temperature 230 ° C

219000 cP@Shear Rate 700 1/s, Temperature 446 ° F

242000 cP@Shear Rate 500 1/s, Temperature 230 ° C

242000 cP@Shear Rate 500 1/s, Temperature 446 ° F

346000 cP@Shear Rate 500 1/s, Temperature 200 ° C

346000 cP@Shear Rate 500 1/s, Temperature 392 ° F

Linear Mold Shrinkage 线性收缩率

0.018 - 0.021 cm/cm@Thickness 3.20 mm

0.018 - 0.021 in/in@Thickness 0.126 in

Flow, 24h; ASTM D955

POM美国杜邦500P物性表, POM美国杜邦500P材质报告, POM美国杜邦500P最新价格, POM美国杜邦500P厂价直销等等