

# 硅酸铝板保温材料隔热材料【湿法】祥雨硅酸铝纤维厂

产品名称	硅酸铝板保温材料隔热材料【湿法】祥雨硅酸铝纤维厂
公司名称	祥雨硅酸铝纤维厂
价格	.00/个
规格参数	耐火温度:1580 ~ 1770 ( ) 产地:东营
公司地址	中国 山东 东营市东营区 南一路
联系电话	86-05468615291

## 产品详情

耐火温度	1580 ~ 1770 ( )	规格	长600*宽400*厚20-50 ( m )
产地	东营	品牌	祥雨
产品类别	窑炉工业窑炉用保温材料	材质	硅酸铝
导热系数 ( 常温 )	0.06-0.16	等级	1
低温弯折	.	断裂伸长率	.
抗弯强度	.	抗压强度	0.5
拉伸强度	.	使用温度	950-1200
撕裂强度	.	芯材	硅酸铝纤维
形态	纤维状	形状	片状

### 产品说明：

采用湿法真空成型工艺加工而成，该类产品的强度高于纤维毯和真空成型毡，适用于对产品有刚性强度要求的高温领域。

### 产品特点：

耐压强度高、使用寿命长；低热容量，低热导率；非脆性材质，韧性好；尺寸精确，平整度好；易切割安装，施工方便；优良的抗风蚀性能；连续化生产，纤维分布均匀，性能稳定；优良的吸音降噪性能。

### 典型应用：

钢铁行业：膨胀缝，被衬隔热、隔热片和铸模隔热；有色金属行业：中间包和流槽盖，用于浇筑铜和铜合金；陶瓷行业：轻质窑车结构与窑炉的热面衬体、窑炉各温度区分隔及挡火材料；玻璃行业：熔池

被衬隔热，烧嘴块；窑炉建筑：热面耐火材料（替代纤维毯），重质耐火材料的被衬，膨胀缝；轻工业：工业与家用锅炉燃烧室的内衬；石化行业：高温加热炉内衬得热面材料

product description:the use of wet processing by a vacuum forming process, the strength of these products is higher than fiber blanket and vacuum molding carpet, apply to steel products are high-temperature strength of the field.features:high strength, long service life; low heat capacity, low heat conductivity; non-brittle material, toughness; size precision, good flatness; easy to cut the installation, construction convenient; good anti-wind performance; continuous production, fiber distribution stable performance; excellent acoustic noise performance.typical applications:iron and steel industry: expansion joints, the lining insulation, thermal insulation and mold insulation film; non-ferrous metals industry: tundish and the flow slot cover for pouring copper and copper alloys; ceramic industry: structure and light trucks kiln kiln surface lining of the body heat, the furnace and the temperature zones separated by fire block material; glass industry: molten pool were lining insulation, burner block; kiln construction: hot face refractories (alternative fiber blanket), heavy refractory by contrast, expansion joints; light industry: industry and domestic boiler combustion chamber liner; petrochemical industry: a high-temperature furnace lining hot face material