

# ZN-2 PIB masterbatch

产品名称	ZN-2 PIB masterbatch
公司名称	佛山市鸿德信电子有限公司
价格	.00/kg
规格参数	
公司地址	三水区西南街道广海大道东8号1005
联系电话	18924563928

## 产品详情

Packed in 20kg/bag, 1400kg/pallet. Keep the place dry with good ventilation. Out of direct sunlight, high temperature, rain pour and no under heavy loads.

Warranty: 1yearUsage:

ZN-2 is designed to produce stretchwrap films from LLDPE, LDPE or for the applications of palletwrap and silagewrap. It can be used on either blown film or cast film process.Polymers used with ZN-2 masterbatch must not contain any Anti blocking additive, slip agent as this will prevent the migration of cling additive. Migration time for good cling properties is usually 24 to 72 hours.

Note: during production, the speeder the film get cool,means stronger adhesion the film surface is; and the more ZN-2 added in, the stronger adhesion get. Production thereafter, should keep the film in a high temperature to enhance the the adhesion as the storge time goes.

### RECOMMENDED ADDITION

On monolayer blown film lines, 6% to 8% ZN-2 by weight should be added to resin mix.

On monolayer Cast lines , 3 % to 5 %

On multiple-layer film lines, ZN-2 is usually added to the skin layers only. Addition level depends on which layer is used and the thickness of layer.Product Index:

appearance	Lightly powdered opaque dry po
% of cling additive	58 - 60%
density	0.902
moisture	<0.5%

