

阴图PS版 铝版

产品名称	阴图PS版 铝版
公司名称	江苏韵燕印刷版材有限公司
价格	.00/个
规格参数	版材:铝版
公司地址	泰兴市经济开发区高新产业园向荣路南首区间路6号
联系电话	0523-87733184 18621585920

产品详情

版材 铝版

negative pre-sensitized offset printing plateintroductionjinyan negative ps plates have high pressrun, proper exposure rate, simple plate making,and perfect dot reproduction advantages and so on. in order to make the plate reach its bestprinting efficiency, please use it under the following conditions.1. printing down(exposure):negative ps plate ' exposure is finished by negative film jointing nearly with sensitive plate,spectrum range is between blue ray and ultraviolet ray (320-450nm), while exposing, the iodinegallium lamp is the most proper lamp-house and around 150mj/c m² exposure quantum isrecommended, in the actual operation, the exposure time can be different according to differentexposure equipment and different film sort. so the exposure time must be decided by actualexperiment result.(1) put fuji gray scale (0.15 tier) on the edge of plate and under the film, choose theproper exposure quantum to expose the plate, after finishing exposing, wash the plate,the optimum exposure quantum can be determined on the ninth step withoutprinting ink.(2) use ugra pcw82 control strip, choose proper exposure quantum to expose it, whenthe 15-20um weenie line appear on the control strip, the exposure quantum reach itsoptimum state.15~20 μ weenie line sketch map(3) remark:in order to reach the most pressrun, the exposure quantum must be enough;in order to prevent halftone (net dot) being scale-up, the exposure quantum can ' t beadded or decreased optionally. avoid the tone value, transferred from film withhalftone to printing plate, increasing excessively and decreasing excessively so thatthe thin part of the dark area disappearing; the tone value must be controlled in thepermitted range.(4) before using our plate to print, please operate it under the yellow safe light toprevent exposing before printing for fear it influences quality.2. developkodak -956 developer and our company ' s negative developer are stronglyrecommended.develop temperature: 25 ± 2 developer ' s dilution ratio: 1:1(developer: water)develop time: 30-60 seconds.manual develop: must scrub, wash off remnant developer on the surface of plate.automatic develop: develop machine must be equipped with brush to reinforcedeveloping efficiency.introduction:(1) because the developer from different area is of diversity, some of negative plate willappear shallow yellow on the surface after developing, with the plate substrate beingusing, the shallow yellow will disappear automatically, it won ' t influence printingeffect (kodak -956 developer has no such problem).(2) in order to solve the problem, you can expose the developed plate once again, thatwill not only eliminate the shallow yellow but also enhance pressrun.3. correction:in order to wipe off the excrescent image and stain, you can lay right quantity negativere mover on the surface of image or stain. 15 seconds later, wash the surface.4. inking up (dip ink):the function of dipping ink to negative plate is to

enhance the image area ' s capability of absorbing ink and enduring fretting. the negative plate must be laid a layer of sensitive colophony additionally on the image area. 5. lay on gum. the gum must be diluted under the manufacturer ' s requirements, and the layer should be well-distributed. too thin or too thick all will influence the effect, and if you lay on gum automatically, please control the drying temperature. 6. storage (1) before using: the negative plates should be stored in the cool (10—30 °C), dark and dry place. relative humidity ≤ 60%. (2) storage life: six months.