

# 雨靴质量检测报告HG/T 2020-测试

产品名称	雨靴质量检测报告HG/T 2020-测试
公司名称	深圳市佰测威检测有限公司
价格	.00/个
规格参数	
公司地址	深圳市龙岗区龙岗区爱联中粮祥云2A505
联系电话	0755-15602437376 15602437376

## 产品详情

产品范围：雨靴，雨鞋

产品标准：HGT 2019-2011 黑色雨靴(鞋)，HGT 2020-2011 彩色雨靴(鞋)

检测项目，产品要求

HGT 2019-2011 黑色雨靴(鞋)

1 Appearance : Black Rain Rubber Boots (Shoes)

外观质量 : 黑色雨靴 (鞋) HG/T 2019 4.6 No major defects

2 Tensile Strength for Outsole

外底拉伸强度 GB/T 528 Upper: Min 10.0 Mpa

Outsole: Min 7.0 Mpa

3 Breaking Elongation

拉断伸长率 GB/T 528 Upper: Min 400%

Outsole: Min 320%

4 Abrasion Test for Outsole

外底磨耗量 GB/T 1689 Outsole: Max 1.2cm

5 Hardness for outsole (shore hardness)

外底硬度 GB/T 531.1 Upper: Max 65 ShoreA

Outersole: Max 70 Shore A

6 Sole bond (outsole and midsole) strength

外底与外中底粘合强度 GB/T 532 Upper: Min 0.4 N/mm

7 Elongation of Film: Black Rain Rubber Boots (Shoes)

漆膜伸長率: 黑色雨靴 (鞋) HG/T 2019 Annex A Upper: Min 100%

8 Tensile Retention After Ageing test

老化和耐热试验 GB/T 3512 Min 80%

9 Thickness of Outsole : Black Rain Rubber Boots (Shoes)

鞋或厚度 : 黑色雨靴 (鞋) HG/T 2019.5.9.1 Shoes size: > 230

Forepart: Min 4.0 mm for rolling; Min 6.0 mm for mould

Base: Min 2.0 mm for rolling; Min 2.5 mm for mould

Heelpart: Min 5.0 mm for rolling; Min 7.0 mm for mould

Shoes size <= 230

Forepart: Min 3.0 mm for rolling; Min 5.0 mm for mould

Base: Min 1.6 mm for rolling; Min 2.0 mm for mould

Heelpart: Min 4.0 mm for rolling; Min 6.0 mm for mould

10 Thickness of Upper : Black Rain Rubber Boots (Shoes)

鞋帮厚度 : 黑色雨靴 (鞋) HG/T 2019 5.9.2 Min 1.0 mm

11 Water Resistance

耐渗水试验 HG/T 3664 No leak

12 Size marking

鞋号 GB/T 3293.1 The marking of size shall be included the length and width of foot, and the height of letter for marking shall be not less than 3 mm.

13 Labeling and packaging

标示及包装 HG/T 2403 Satisfactory

## HGT 2020-2011 彩色雨靴(鞋)

No. Test Items Test Method GB Test Requirement

(Pass Grade)

1 Appearance : Color Rain Rubber Boots (Shoes)

外观质量 : 彩色雨靴 (鞋) HG/T 2020 4.6 No major defects

外底拉伸强度 GB/T 528 Upper: Min 10.0 MPa Outsole: Min 7.0 Mpa

拉断伸长率 GB/T 528 Upper: Min 400% Outsole: Min 320%

外底磨损量 GB/T 1689 Outsole: Max 2.1 cm