

Protexior 794耐化学环氧树脂

产品名称	Protexior 794耐化学环氧树脂
公司名称	上海恩莱保贸易有限公司
价格	.00/个
规格参数	
公司地址	上海市松江区金高路2388号813室
联系电话	86-021-20228098 13391171050

产品详情

Protexior794耐化学环氧树脂Protexior 794 Chemical Resistant Epoxy

SKU794

Common Uses

Transformers and vessels

Containment areas

Valves, piping and pumps

Ducts, Plenums and Baghouses

Specification Data

Generic TypeEpoxy

ColorBlack

Continuous Temperature350 ° F (177 ° C)

Components2

Volume Solids60 ± 2%

Dry Film Thickness per coat4.0 to 5.0 mils

Wet Film Thickness per coat6.6 to 8.3 mils

Application Method

Spray|Brush|Roll

Theoretical Coverage 962 sq. ft. @ 1 mil

Dry to Touch 12 hrs

Dry Time to Recoat 12 to 14 hrs

Dry Time to Ship 7 days at 75 ° F (23.9 ° C)

VOC Content 0.75lbs/gal